

Technical Data Sheet
Typical Application — General Purpose

Premi-Glas® 1100-15 is a fiberglass reinforced thermoset bulk molding compound for general purpose applications requiring thermal stability and stiffness.

Key Features and Benefits:

- Excellent stiffness to weight ratio, non-melting.
- Good dimensional stability, including excellent thermal resistance.
- Pigmentable for molded-in color; best appearance with mold texture.
- Excellent property retention in cold and hot environments.
- Good corrosion resistance except in acid environments.

| Typical Values. Mechanical values are for Specimens cut from Compression-Molded panels. | | | |
|---|-------------|---------------------------|-----------------|
| Properties | Test Method | Values (US) | Values (Metric) |
| Flexural Strength | ASTM D-790 | 14,000 psi | 95 MPa |
| Flexural Modulus | ASTM D-790 | 1.4 x 10 ⁶ psi | 9.7 GPa |
| Tensile Strength | ASTM D-638 | 4,500 psi | 31 MPa |
| Tensile Modulus | ASTM D-638 | 2.0 x 10 ⁶ psi | 14 GPa |
| Notched Izod | ASTM D 256 | 6 ft*lb/in | 370 Joules/m |
| Unnotched Impact | ASTM D 4812 | 9 ft*lb/in | 480 Joules/m |
| | | | |
| | | | |
| | | | |
| | | | |
| | | | |
| | | | |
| | | | |
| | | | |
| | | | |
| | | | |

This BMC product is generally intended to be compression or injection molded in matched metal die molds, typically at 300°F (150°C) and 500 to 1000 psi (35-65 BAR) molding pressure. Strength values may be affected by the molding process. Nominal values for polymerization shrinkage (0.0015 to 0.0035 in/in) and specific gravity (1.70 to 1.85) may be customized for individual applications. Contact your Premix sales representative for specific design recommendations.

Following physical characteristics are typical of this product:

| |
|-------------------------------------|
| CLTE, XY direction: 25 ppm/ deg C |
| CLTE, Z direction: 35 ppm/deg C |
| Thermal Conductivity: 0.3 W/m*deg K |
| Poisson's Ratio: 0.3 |

The values presented in this data sheet are typical values and are not to be interpreted as product specifications.
All statements, information and data given herein are believed to be accurate and reliable but are presented without guarantee, expressed or implied.

Last modified: 7/29/2009